
THE MELTING POINT

| | |
|---|-----------------|
| ALUMINUM (3000 SERIES & 1100 ALLOYS) | 1175°F - 1210°F |
|---|-----------------|

| | |
|-----------------------|-----------------|
| T-304 STAINLESS STEEL | 2550°F - 2650°F |
|-----------------------|-----------------|

| | |
|-----------------------|-----------------|
| T-316 STAINLESS STEEL | 2500°F - 2550°F |
|-----------------------|-----------------|

**NOTE: TENSILE STRENGTH WILL DIMINISH AS
TEMPERATURE INCREASES.**

THE ABOVE INFORMATION IS NOT INTENDED FOR DESIGN PURPOSES.